

**OVERVIEW**

Supertex is a two coat exterior coating which gives a luxurious gloss finish coupled with a variety of texture type dependent on application method. It is an acrylic coating and was specifically developed for use in areas of extreme climatic conditions. Supertex is highly resistant to dirt pick-up from the atmosphere thereby keeping building facades clean for many years. This system also allows water vapour to pass from the structure to the atmosphere but will not allow water ingress.

**PRODUCT GRADES/CODES**

|          |       |
|----------|-------|
| Topcoat  | 61130 |
| Basecoat | 61650 |

**PROPERTIES**

Supertex Basecoat is formulated from crushed and precisely graded fillers, pure acrylic binders and additives which give it elastic properties. Supertex Topcoat is formulated from high quality pigments and binders which give it elastic properties, long life, fade resistance and an attractive gloss finish.

By utilising different rollers and various spray techniques the basecoat may be applied in various texture types. The topcoat is available in an attractive range of colours.

**AREA OF USE**

Supertex is primarily designed for exterior facades and surfaces of buildings such as commercial and industrial complexes, office projects, hospitals and housing development. It gives an attractive glossy texture to fairfaced concrete walls, pillars, columns etc. Supertex can be used on all concrete surfaces, rendering, lightweight concrete, stonework, brickwork, blockwork, plywood, antirust primed steel and galvanised steel. It can be used to renovate previously painted buildings. It performs equally well on interior surfaces of gypsum, dry-wall and chipboard etc.

**PREPARATION OF SURFACE**

Ensure that all dust, dirt and foreign matter are brushed and scraped away. Also ensure the surface is free from salt, grease, oil and ridges. Protect all adjacent areas not to be covered. Surface can be repaired with Terramix and Acrylic filler. Dusty surface should be treated with Penetrating Primer. Old surfaces should be treated with a soda / water solution, rinsed and allowed to dry before application of Supertex.

**APPLICATION & CLEANING OF TOOLS**

Supertex Basecoat can be applied using spray or roller to achieve the required texture. Allow the basecoat to dry for 24 hours and then apply two coats of topcoat. The first coat can be diluted with 30% water. The second coat should not be diluted.

Clean tools and equipment with water after use.

**HEALTH & SAFETY**

Avoid prolonged contact with eyes and skin. For detailed information refer to relevant material safety data sheet.

**PACKAGING & STORAGE**

Supertex Basecoat, Supertex Topcoat are supplied in 25 kg conipails.

Store containers in a clean dry area protected from direct sunlight and extreme heat and cold. Unopened containers can be stored for 12 months. Use oldest material first.

TERRACO offers a comprehensive range of products and services for most concrete and finishing needs. Please contact the TERRACO Technical Service Department or your local TERRACO agent for further information, samples, demonstrations and instructor services. The information given in this leaflet is based upon laboratory research, as well as extensive field work and application. All products are sold subject to standard conditions of sale which are available on request. This information is based on TERRACO's present state of knowledge and is intended to provide general information on TERRACO's products and their methods of use. The prospective user is recommended to determine the suitability of TERRACO's suggestions and products before adopting them on a commercial scale.

**TECHNICAL DATA**

|                           |   |              |
|---------------------------|---|--------------|
| <b>Product</b>            | Acrylic based gloss textured coating system.  |              |
| <b>Binder</b>             | Acrylic co-polymer.   |              |
| <b>Pigments</b>           | Lime and light fast.  |              |
| <b>Thinning</b>           | Water if required.  |              |
| <b>Primer</b>             | Use <i>TERRACO</i> Penetrating Primer.  |              |
| <b>Drying Time</b>        | Basecoat  | 3 - 4 hours. |
|                           | Topcoat   | 1 - 2 hours. |
| <b>Toxicity</b>           | Non-toxic.  |              |
| <b>Specific Gravity</b>   | Basecoat  | 1.75 ± 0.05  |
|                           | Topcoat   | 1.20         |
| <b>Coverage</b>           | Basecoat 1-1.15m <sup>2</sup> /ltr depending on texture required.<br>Topcoat 8-12 mt <sup>2</sup> /ltr. |              |
| <b>Application Method</b> | Spray or roller.  |              |
| <b>Colour</b>             | Available in 20 standard shades.  |              |
| <b>Packaging</b>          | 25 kg conipails.  |              |
| <b>Storage</b>            | 12 months in original unopened containers.  |              |

For technical enquiries please contact your nearest Terraco representative:

**CHINA:**

Terraco Architectural Coatings China Co., Ltd.  
Tel: +86 (0)20 8759 4742  
Fax: +86 (0)20 8526 8056  
E-mail: sales@terraco.com.cn  
Web: www.terraco.com.cn

**Terraco Chemical (Shanghai) Co., Ltd.**

Tel: +86 (0)21 621020 48 / 18  
Fax: +86 (0)21 625205 47  
Email: sales@terraco.com.cn  
Web: www.terraco.com.cn

**EGYPT:**
**Terraco Egypt Chemical Industries S.A.E.**

Tel: +20 (0)22 29184 53 / 57 / 58  
Fax: +20 (0)22 29184 80  
E-mail: terraco@terraco.com.eg  
Web: www.terraco.com.eg

**JORDAN:**
**Jordan Swedish Polymers Industrial Corp.**

Tel: +962 (0)6 553 8751  
Fax: +962 (0)6 553 6560  
E-mail: terraco@nol.com.jo  
Web: www.terraco.jo

**IRELAND:**
**Terraco Technical Centre, Ireland**

Tel: +353 (0) 404 66555  
Fax: +353 (0) 404 66654  
E-mail: technical-centre@terraco.com  
Web: www.terraco.com

**PAKISTAN:**
**Terraco Pakistan Pvt. Ltd.**

Tel: +92 (0)42 3529 70 56-8  
Fax: +92 (0)42 3529 70 55  
Email: terraco@terraco.pk  
Web: www.terraco.com

**ROMANIA:**
**Terraco Romania SRL**

Tel: +40 (0)749 203 133  
Fax: +40 (0)318 148 810  
E-mail: ahaque@terraco.com  
Web: www.terraco.com

**RUSSIA:**
**OOO Terraco Sweden Ltd, Russia**

Tel: +7 (0)495 9212 237  
Fax: +7 (0)495 6273 881  
E-mail: adm@terraco.ru  
Web: www.terraco.ru

**OOO Terraco Vostok Ltd**

Tel: +7 (0)4212 410563  
Fax: +7 (0)4212 410591  
E-mail: terracovostok@terraco.khn.ru  
Web: www.terraco.com

**SOUTH KOREA:**
**Terraco Korea Co., Ltd**

Tel: +82 (0) 2 5611 551  
Fax: +82 (0)2 5671 771  
E-mail: terraco@terraco.co.kr  
Web: www.terraco.co.kr

**THAILAND:**
**Terraco Industry (Thailand) Limited**

Tel: +66 (0)2 946 68 56 / 58  
Fax: +66 (0)2 946 68 59  
E-mail: terraco@terraco.co.th  
Web: www.terraco.com

**TURKEY:**
**Terraco Yapi Malzemeleri Sanayi Ve Ticaret AS**

Tel: +90 (0)222 236 0423  
Fax: +90 (0)222 236 0425  
E-mail: terraco@terraco.com.tr  
Web: www.terraco.com.tr

**UAE:**
**Terraco UAE Ltd**

Tel: +971 (0)4 326 2699  
Fax: +971 (0)4 326 2733  
E-mail: terraco@terraco.ae  
Web: www.terraco.com

**UK:**
**ADDAGRIP**

Tel: +44 (0)1825 761 333  
Fax: +44 (0)1825 768 566  
E-mail: sales@addagrip.co.uk  
Web: www.addagrip.co.uk / www.terraco.com

**VIETNAM:**
**Terraco Vietnam Co., Ltd**

Tel: +84 (0)650 3 820 100  
Fax: +84 (0)650 3 820 101  
E-mail: terraco@terraco.com.vn  
Web: www.terraco.com